

**AMENDMENTS TO THE CLAIMS:**

Please replace the claims with the claims provided in the listing below wherein status, amendments, additions and cancellations are indicated.

1. - 10. (Canceled)

11. (Currently Amended) Self-adhesive sheet for bonding a floor covering to a floor, consisting of:

a backing layer having a top surface adapted to face the floor covering and a bottom surface adapted to face the floor;

a first pressure-sensitive adhesive coating coated on the entire top surface of said backing layer, said coated top surface of said backing layer being planar and being adapted to adhere to the floor covering; and

a second pressure-sensitive adhesive coating coated on the bottom surface of said backing layer, said coated bottom surface of said backing layer being planar and being adapted to adhere to the floor, said first pressure-sensitive adhesive coating having a different adhesive strength than said second pressure-sensitive adhesive coating and the adhesive strength of said second pressure-sensitive adhesive coating being lower than the adhesive strength of said first pressure-sensitive adhesive coating,

a removable cover film removably adhered to the coated top surface of said backing layer;

said backing layer comprising a polymer film,

F6817 Am 08 (PL14) wpd

Docket No. F-6817

Ser. No. 09/762,530

the self-adhesive sheet having planar top and bottom surfaces consisting of said respective first and second adhesive coatings exposed and having a minimum width of 350 mm for extensive coverage of the floor to be covered with the floor covering.

12-15. (Cancelled)

16. (Currently Amended) Self-adhesive sheet of claim ~~according to one of Claims 11 to 14~~, wherein the adhesive strength of said second adhesive coating expressed as adhesive force, measured in accordance with DIN 1939, is about from 0.8 to 5 N.

17. (Currently Amended) Self-adhesive sheet of claim ~~according to one of Claims 11 to 14~~, wherein the different adhesive strength said first and second adhesive coatings is brought about by different adhesive application rates expressed as weight of adhesive per unit area of surface, the surface with the greater adhesive strength having a higher adhesive application rate.

18. (Currently Amended) Self-adhesive sheet of claim ~~according to one of Claims 11 to 14~~, wherein said first pressure-sensitive adhesive coating comprises

Docket No. F-6817

Ser. No. 09/762,530

pressure-sensitive adhesive different from the pressure-sensitive adhesive coating of said second pressure-sensitive adhesive coating.

19. (Previously Presented) Self-adhesive sheet according to Claim 17, wherein the adhesive application rate on the top surface is in a range from 100 to 250 g/m<sup>2</sup> and on the bottom surface is in a range from 5 to 40 g/m<sup>2</sup>.

20. (Cancelled)

21. (Currently Amended) Self-adhesive sheet of claim ~~according to any of Claims 11 to 14~~, wherein the width of the self-adhesive sheet is in a range from 350 mm to 2000 mm.

22. (Previously Presented) Self-adhesive sheet according to claim 16, wherein the adhesive strength of said second adhesive coating expressed as adhesive force is about 1.5 N to 3 N.

23. (Previously Presented) Self-adhesive sheet according to claim 22, wherein the adhesive strength of said second adhesive coating expressed as adhesive force is about 2.0 N to 2.6 N.

Docket No. F-6817

Ser. No. 09/762,530

24. (Previously Presented) Self-adhesive sheet according to claim 19, wherein the adhesive application rate on the bottom surface is about 8 to 20 g/m<sup>2</sup>.

25. (Previously Presented) Self-adhesive sheet according to claim 21, wherein the width of the self-adhesive sheet is in a range of from 500 mm to 1500 mm.

26. (Previously Presented) Self-adhesive sheet according to claim 25, wherein the width of the self-adhesive sheet is in a range of from 600 to 1000 mm.

27. (Currently Amended) A method for bonding a floor covering to a floor comprising:

coating an entire ~~a~~ top surface of a backing layer comprising polymer film with a first pressure-sensitive adhesive coating to form a coated top surface of the backing layer which is planar, and

coating a bottom surface of the backing layer with a second, planar pressure-sensitive adhesive coating to form a coated bottom surface of the backing layer which is planar, the first pressure-sensitive adhesive coating having a different adhesive strength than the second pressure-sensitive adhesive coating and the adhesive strength of the second pressure-sensitive adhesive coating being lower than the adhesive strength of the first pressure-sensitive adhesive coating,

Docket No. F-6817

Ser. No. 09/762,530

thereby to produce a self-adhesive sheet having planar top and bottom surfaces and consisting of a backing layer the top surface of which is coated with the first pressure-sensitive adhesive coating and the bottom surface of which is coated with the second pressure-sensitive adhesive, and

adhering a removable cover film to the coated top surface of said backing layer;

adhering the bottom surface of the self-adhesive sheet to the floor by means of the second pressure-sensitive adhesive coating, and

adhering the floor covering to the self-adhesive sheet by means of the first pressure-sensitive adhesive coating.

28. (Previously Presented) A method according to claim 27, wherein the floor covering is a carpet.

29. (Previously Presented) A method according to claim 28, wherein the floor is parquet.

30. (Previously Presented) Self-adhesive sheet according to claim 11, wherein said backing layer is made of propylene or polyethylene film.

Docket No. F-6817

Ser. No. 09/762,530

31. (Previously Presented) Self-adhesive sheet according to claim 11, further comprising a first textile structure arranged on the top surface of said backing layer and a second textile structure arranged on the bottom surface of said backing layer.